





Technical properties:

Basic material	Synthetic dispersions
Consistency	Paste
Polymerization	Physical Polymerization
Open time	10 - 15 min.
Drying time	Approx. 24 hours
Density (DIN 53479)	1.6 g/ml
Temperature resistance (after hardening)	-20°C up to + 70°C
Consumption	70 – 150 ml/m of moulding

Product:

ADEFIX® is a white acrylic adhesive-filler.

Characteristics:

- Solvent free
- Retains slight elasticity after drying
- Suitable for application on porous substrates
- Can be sanded
- Can be painted
- For indoor use
- Not frost-resistant

Applications:

Adhesive, filler and jointing material for NOMASTYL®, WALLSTYL® polystyrene products and ARSTYL® polyurethane products.

www.nmc.eu



NMC sa reserves the right to update the product line or its technical features to the state-of-the-art technology anytime and without previous announcement. All given information is to the best of our knowledge. If you have any questions concerning technical details please contact the NMC sa information service. Any partial reproduction or reprint shall require our explicit approval.

NMC sa

Gert-Noël-Straße - B-4731 Eynatten

Tel.: +32 87 85 85 00 Fax: +32 87 85 85 11 E-Mail: info@nmc.eu



ADEFIX® Glue 310 ml



Packaging:

■ Colour: white

■ Content: cartridge of 310 ml

Shelf-life:

Can be stored for 24 months in its sealed package in a cool, dry place at +5°C to +25°C.

Substrates:

- Nature: porous materials such as brick, concrete, plaster.
- Condition: the substrate must be clean, dry, stable, and free of dust and grease. We recommend testing gluing on all substrates.

Method of use:

- Application: apply adhesive liberally to the gluing surfaces with an applicator gun (cartridge) or spatula. Then place the decorative element onto the substrate and press. Use ADEFIX® adhesive for NOMASTYL® and smaller WALLSTYL® and ARSTYL® coving edges and joints. Wipe away surplus adhesive with a spatula or wet sponge. Use ADEFIX® PLUS adhesive for WALLSTYL® and ARSTYL® coving edges and joints from 10 cm height/projection and finish with ADEFIX® (see installation instructions). Prop up if needed.
- Width of joints: between the individual profiles approx. 2-3 mm.
- Application temperature: +5°C to +35°C
- Cleaning product (before hardening): water

Comments:

It is preferable that the substrate is porous, stable and not painted.

Safety measures:

Follow the usual Occupational Health & Safety procedures.