


ADEFIX® P5

Glue 310 ml, 1 kg, 5 kg



Technical properties:

Basic material	Plastic dispersions
Consistency	Paste
Polymerization	Physical polymerisation
Open processing	10-15 min.
Drying time	Approx. 24 hours
Density	1.81 g/ml
Temperature resistance	-20°C to +70°C (after hardening)

Product:

ADEFIX® P5 is an adhesive filler for fixing polystyrene, NOMASTYL®, and polyurethane, ARSTYL®, covings and ceiling medallions.

Characteristics:

- Solvent free
- Retains slight elasticity after drying
- Can be sanded
- Suitable for painting
- Not frost-resistant

Applications:

Sticking and pointing extruded or expanded polystyrene and polyurethane on walls and ceilings, in porous substrates.



NMC sa reserves the right to update the product line or its technical features to the state-of-the-art technology anytime and without previous announcement. All given information is to the best of our knowledge. If you have any questions concerning technical details please contact the NMC NMC sa information service. Any partial reproduction or reprint shall require our explicit approval.

NMC sa
Gert-Noël-Straße - B-4731 Eynatten
Tel.: +32 87 85 85 00
Fax: +32 87 85 85 11
E-Mail: info@nmc.eu

www.nmc.eu



ADEFIX® P5

Glue 310 ml, 1 kg, 5 kg



Packaging:

Colour: white

Package size: Cartridge of 310 ml, buckets of 1 kg and 5 kg

Shelf life:

Will keep in its a sealed package in a cool, dry place at +5°C to +25°C for 24 months.

Substrate:

Material: porous materials such as brick, concrete, plaster.

The substrate must be clean, dry and free of dust or grease.

Method of use:

Apply with an applicator gun (cartridge) or spatula.

Coat the gluing surfaces of the decorative elements.

Then place the decorative element onto the substrate and press hard.

Application temperature: +5°C to +30°C.

Cleaning: Water, only in fresh state.

Width of joints: Between the individual profiles approx. 2-3 mm.

Comments:

It is preferable that the substrate is porous.

Safety measures:

Follow the usual Occupational Health & Safety procedures.